

DSC INOX-S®

BALBACH DAMAST®

ÉTAT DE LIVRAISON

- Recuit (22-27HRC)
- Laminé à chaud/rectifié

COMPOSITION

Nuance	cou- leur	C	Si	Mn	P	S	Cr	Mo
Sandvik 7C27Mo2	foncé	0.38%	0.4%	0.6%	<0,025%	<0,01%	13.5%	1%
Sandvik 19C27	clair	0.95%	0.4%	0.7%	<0,025%	<0,01%	13.5%	-

CARACTÉRISTIQUES

- Soudures des couches SuperClean
- Résistant à la corrosion
- Grain très fin
- Forte tenue du tranchant
- Haute dureté (jusqu'à 62Hrc)
- Très faible déformation après trempe



Produit apte au contact alimentaire

EMPLOIS PRINCIPAUX

Lames et pièces de couteaux, outils tranchants, bijouterie/joaillerie

NORMES

(correspondances approximatives)

AFNOR	WNR	AISI
7C27Mo2	-	-
19C27	-	-

TRAVAIL À CHAUD / FORGEAGE

TEMPÉRATURE DE TRAVAIL : 950-1050°C

RECUIT

Pour travailler la matière après forgeage, il faut procéder à un recuit à doux selon les étapes suivantes :

- Chauffer au four 830°C
- Maintien 4h minimum
- Refroidissement lent au four
- Sortir du four quand température <400°C

TRAITEMENT THERMIQUE

Cryo non obligatoire mais recommandé.


TEMPÉRATURE DE TREMPE : 1050-1060°C

TEMPS DE MAINTIEN : 15 minutes sous papillote ou atmosphère protégé

REFROIDISSEMENT RAPIDE À L'AIR

REVENU : 150-180°C pendant 2 x 1 heure pour une dureté de 60/61 HRC

COURBE DE REVENU



Veillez noter que l'acier Damas créé a son propre profil de dureté se trouvant entre les deux aciers qui le composent.

RÉVÉLATION

Pour obtenir une révélation optimale :

- Polissage fin/polé miroir après trempe
- Nettoyer/dégraisser (liquide vaisselle/acétone)
- Révélation (voir ci-dessous)
- Neutralisation
- Second polissage fin (grain>2000) jusqu'à obtention du contraste souhaité

Vous pouvez révéler nos damas dans différents acides. Pour obtenir un bon résultat, chauffer l'acide à 50°C. Nous recommandons une révélation profonde pour obtenir une bonne différence entre les couches.

	acide	dénomination chimique
1	Acide sulfurique (15-30%)	H ₂ SO ₄
2	Perchlorure de fer (15-35%)	FeCl ₃

 Portez des protections (gants, lunettes...). A réaliser dans un endroit ventilé

SIÈGE SOCIAL

EUROTECHNI S.A.S
Agence de Racine
Z.A Racine
63650 La Monnerie-le-Montel

AGENCE DE NOGENT

EUROTECHNI S.A.S
Agence de Nogent
40, Rue du Guay
52800 Nogent

 TEL : +33 (0)4 73 51 44 77

DSC INOX-S®

BALBACH DAMAST®

STATE OF DELIVERY

- Annealed (22-27HRC)
- Hot rolled/rectified

ANALYSIS

Shade	color	C	Si	Mn	P	S	Cr	Mo
Sandvik 7C27Mo2	dark	0.38%	0.4%	0.6%	<0,025%	<0,01%	13.5%	1%
Sandvik 19C27	light	0.95%	0.4%	0.7%	<0,025%	<0,01%	13.5%	-

SPECIFICATIONS

- SuperClean-layer welds
- Easy working
- Very fine grain
- High edge holding
- High hardening possible (up to 63Hrc)
- Uncritical misforming after heat treatment



Product suitable
for food contact

MAIN USES

Blades and knife parts, cutting tools, jewelery

STANDARDS

(approximate equivalent)

AFNOR	WNR	AIISI
7C27Mo2	-	-
19C27	-	-

HOT WORKING

WORK TEMPERATURE : 950-1050°C

ANNEALING INFORMATION

To work the material after forging, it is necessary to carry out a soft annealing according to the following steps :

- Heat in the oven 830°C
- Hold 4 hours minimum
- Slow cooling in the oven
- Remove from the oven when temperature <400°C

HEAT TREATMENT

Cryo not required but recommended.


HOT WORKING : 1050-1060°C

HOLD TIME : 15 minutes under foil or protected atmosphere

FAST QUENCHING WITH OIL

TEMPERING : 150-180°C pendant 2 x 1 heure pour une dureté de 60/61 HRC

TEMPERING CHART



Please note that a new material with its own hardness profile is created through the composition of Damascus steel.

ETCHING INFORMATION

In order to achieve a perfect etching result :

- Fine polish and mirror polish after hardening
 - Remove contaminations and possible fats with e.g. dishwashing liquid/acetone
 - Etching process (see below)
 - Neutralize
 - Second fine polish or fine grinding (grade>200) until desired contrast is achieved
- You can etch our damascus in different acids. To obtain a good result, heat the acid to 50 ° C. We recommend a deep revelation to get a good difference between layers.

	acid	chemical name
1	Sulfuric acid (15-30 %)	H ₂ SO ₄
2	Iridium (III) chloride (15-35 %)	FeCl ₃

 Wear protections (gloves, glasses ...). To realize in a ventilated place

HEADQUARTERS

EUROTECHNI S.A.S
Thiers Agency
Z.A Racine
63650 La Monnerie-le-Montel

NOGENT AGENCY

EUROTECHNI S.A.S
Nogent Agency
40, Rue du Guay
52800 Nogent

 TEL : +33 (0)4 73 51 44 77